

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
2 August 2001 (02.08.2001)

PCT

(10) International Publication Number
WO 01/55229 A1

(51) International Patent Classification⁷: C08F 8/32

(21) International Application Number: PCT/EP01/00467

(22) International Filing Date: 16 January 2001 (16.01.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
00200252.5 25 January 2000 (25.01.2000) EP

(71) Applicant: AKZO NOBEL N.V. [NL/NL]; Velperweg 76,
NL-6824 BM Arnhem (NL).

(72) Inventors: IHRIG, Klaus; Rohlederstrasse 4a, 69429
Waldbrunn (DE). BERGFELD, Manfred; August-Pf-
efferstrasse 6, 63906 Erlenbach-Meichenhard (DE).
WECKER, Ulrich; Stegerwaldstrasse 28, 65929 Frank-
furt (DE).

(74) Agent: SCHALKWIJK, Pieter, Cornelis; Akzo Nobel
N.V., Intellectual Property Department (Dept. AIP), P.O.
Box 9300, NL-6800 SB Arnhem (NL).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ,
DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR,
HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR,
LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ,
NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM,
TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian
patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European
patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE,
IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF,
CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: PROCESS TO MAKE AMINATED POLYOLEFINS

(57) Abstract: The invention relates to a process to make aminated polyolefins involving the steps of: ozonolysis of one or more low-molecular weight polyolefin with at least one end group that is unsaturated, in the presence of an alkanol-hydrocarbon mixture, to form polyolefin-alkoxyhydroperoxides, catalytic reduction of the polyolefin-alkoxyhydroperoxides with hydrogen and a suitable catalyst, to form a mixture of hemiacetals and hemiketals, in the presence of a solvent, removal of the catalyst and optional washing of the mixture resulting from step 2, to remove undesired side products, reductive amination of the hemiacetal hemiketal mixture to form the aminated polyolefin end product, preferably at a temperature of 50-200 °C, optionally in the presence of a solvent, and removal of the catalyst and optional removal of the solvent. The aminated products obtained are pre-eminently suited for use as an adjuvant in oils and fuels.



WO 01/55229 A1

PROCESS TO MAKE AMINATED POLYOLEFINS

The present invention relates to a new process to make aminated polyolefins, particularly aminated polyisobutylenes.

5

Aminated polyisobutylenes have long been used as an additive in lubricating oils and/or fuels, such as gasoline, especially unleaded gasoline. Early on, these products were made by halogenation and subsequent amination of low-molecular weight polyolefins, as described in for instance GB 1,083,610.

10 Because of the desire not to use a halogenation process, other routes to the aminated polyolefins were sought.

GB 1,172,818 discloses a process wherein a long-chain ketone or aldehyde, which may be formed through ozonolysis of an olefin polymer and subsequent decomposition of the products formed, is reacted with one or more specific
15 diamines. Specific types of aminated polyolefins are obtained. This process was found to be cumbersome, especially because first the ketone or aldehyde has to be formed and purified. Although conventional techniques are used, this decomposition step is elaborate and costly.

EP-A-0 123 424 discloses employing a specific oxidation process which
20 involves the use of at least one hydroperoxide and at least one peroxide, to oxidize an olefinic polymer which is separated from the reaction mixture. Preferably, the so-oxidized polymers are further reacted with ammonia or organic amines other than tertiary compounds. The use of ammonia in this process resulted in aminated polyolefins with favourable properties. However,
25 the process to make them is not very economical, since it requires the use and handling of at least two types of peroxides.

US 4,832,702 deals with the difficulties observed in the various oxidative processes by introducing a hydroformylation step. The products differ from the previous aminated polyolefins in that an additional carbon atom is introduced
30 into the molecule. This process has gained commercial significance even

though it is not very economical. The process is particularly uneconomical if aminated polyisobutylenes are made, because polyisobutylene with an isobutylene end group, which is present for about 25% in commercial polyisobutylenes, shows poor conversion in the hydroformylation process.

5 US 5,103,061 discloses a process wherein a low-molecular weight polyolefin is first treated with ozone and the resulting product is reacted directly with a primary hydrocarbyl amine. After further treatment aminated polyolefins are obtained. This process is considered to be hazardous even if the ratio of ozone to olefin is selected properly, especially because the primary products of the
10 ozonation are described to be refluxed without taking any precautions.

US 5,274,182 introduces another alternative process in which a high-molecular weight isobutylene-diene copolymer is degraded by means of ozone, the degradation products having two lateral functional groups. These groups can be modified, *inter alia*, with the aid of ammonia in order to obtain specific
15 aminated polyisobutylenes. However, the handling of the very high-molecular weight product can be difficult and use is to be made of the specific copolymer. It is noted that the degradation products of the ozonolysis are stabilized to prevent further oxidation because of the peroxides that are present. The introduction of such additives is time consuming, expensive and for those
20 reasons regarded to be undesired.

Since the aminated polyolefins are of increasing interest for use in modern-day oils and fuels, a new process was sought that: i) does not suffer from the hazards of the above-mentioned processes, ii) can be derived from off-the-shelf
25 low-molecular weight polyolefins, iii) gives good yield, also if polyisobutylenes with an isobutylene end group are used as a raw material, iv) can be practised without the necessity of purifying intermediates and/or adding additional chemicals, and v) preferably can be run in a continuous fashion.

Surprisingly, we have found that a new process fulfills most, if not all, of these requirements. This new process, the first embodiment of the present invention, includes an ozonolysis, a reduction, and a reductive amination step. More particularly, the process involves the steps of:

1. ozonolysis of one or more low-molecular weight polyolefins with at least one end group that is unsaturated, in the presence of an alkanol-hydrocarbon solvent mixture, to form a solution/dispersion of polyolefin-alkoxyhydroperoxides,
2. subsequent catalytic reduction of the crude solution/dispersion of polyolefin-alkoxyhydroperoxides with hydrogen and a suitable catalyst, to form a solution/dispersion of hemi-acetals and or -ketals,
3. removal of the catalyst and optional washing of the mixture resulting from step 2, to remove undesired side products,
4. reductive amination of the hemiacetals and or -ketals to form the aminated polyolefin end product, preferably at a temperature of 50-200°C, optionally in the presence of a solvent, and
5. removal of the catalyst and optional removal of the solvent.

The ozonolysis is conducted in a conventional way, using conventional equipment. Suitably, ozone gas and an optional diluent gas, such as oxygen or air, are bubbled through a solution/dispersion of the unsaturated low-molecular weight polyolefin in the hydrocarbon/alkanol solvent mixture. Part of the acetone and formaldehyde formed will remain in the mixture, while the rest may be carried off, together with some solvent, with the optional diluent gas. Traces of formic acid may form. Preferably, conditions are chosen such that throughout the reaction the mixture is in the form of a solution. In that case, the ozonolysis time can be kept short. Furthermore, it is preferred to conduct the ozonolysis in

- a continuous fashion. In an non-optimized experimental set-up where the ozonolysis was conducted in a continuous fashion at 0-20°C, average residence times of 30 seconds were shown to be sufficient to get a conversion of the unsaturated groups of >95%. Preferably, the ozonolysis is conducted in such a fashion that essentially no formaldehyde is formed by either selecting the appropriate low-molecular weight polyolefin or the proper reaction conditions, e.g. by lowering the ozone concentration, which measures are either known to the skilled person or found by routine experimentation.
- 10 The low-molecular weight polyolefin with at least one unsaturated end group that is used as raw material is preferably selected from the group consisting of polypropene, polyisobutene, poly-1-butene, ethene-propene copolymer, ethene-isobutene copolymer, ethene-1-butene copolymer, propene-isobutene copolymer, propene-1-butene copolymer, and terpolymers of ethene, propene
- 15 and/or butene with one or more other ethylenically unsaturated monomers, such as styrene, α -methylstyrene, vinyl naphthalene, butadiene, and isoprene, with at least one unsaturated ethenyl ($-\text{CH}=\text{CH}_2$), 1-propenyl ($-\text{CH}=\text{CH}-\text{CH}_3$), 2-propenyl ($-\text{CH}_2-\text{CH}=\text{CH}_2$), 1-isobutenyl ($-\text{CH}=\text{C}(\text{CH}_3)_2$), 2-isobutenyl ($-\text{CH}_2-\text{C}(\text{CH}_3)=\text{CH}_2$), 2-butenyl ($-\text{CH}_2-\text{CH}=\text{CH}-\text{CH}_2$), or 3-butenyl
- 20 ($-\text{CH}_2-\text{CH}_2-\text{CH}=\text{CH}_2$) end group. Preferably, it is a polyisobutene, poly-1-butene, or a co- or ter-polymer with 30% or more, preferably 50% or more, monomeric units derived from 1-butene or isobutene, with one of the indicated end groups. More preferably, it is a polyisobutene with 1-isobutenyl ($-\text{CH}=\text{C}(\text{CH}_3)_2$) and/or 2-isobutenyl ($-\text{CH}_2-\text{C}(\text{CH}_3)=\text{CH}_2$) end groups. Most preferred are commercial
- 25 mixtures of said polyisobutenes with said 1-isobutenyl and/or 2-isobutenyl end groups. For ease of production and for increased purity of the product it is preferred to use a low-molecular weight unsaturated polyolefin with just one unsaturated end group.

The number averaged molecular weight (M_n) of these low-molecular weight unsaturated polyolefin materials preferably is from 300 to 5000 Dalton. More preferably, they have a M_n of 400-3000, most preferably from 500-2000 Dalton. An example of a preferred low-molecular weight unsaturated polyolefin is
5 Glissopal® 1000 of BASF.

The alcohol of the solvent mixture may be any linear or branched C_{1-12} alkanol. Preferably, it is a linear or branched C_{1-4} alcohol, such as ethanol, propanol-1, isopropanol, any butanol isomer, or mixture thereof. However, also C_{1-20} diols,
10 triols and/or ether alcohols can be used, such as ethylene glycol, propylene glycol, diethylene glycol, glycerol, and ethoxylated and/or propoxylated glycerol. Preferably, a C_{1-4} alcohol is used, ethanol being most preferred.

The hydrocarbon of the solvent mixture may be any linear or branched C_{4-20} hydrocarbon. Preferably, the hydrocarbon is aliphatic. More preferably, it is a
15 C_{5-10} alkane, hexane and heptane being most preferred.

The alcohol and the hydrocarbon can be used in any ratio, provided at least 5% by weight of the low-molecular weight unsaturated polyolefin dissolves therein at 20°C. The preferred ratio will depend on the low-molecular weight unsaturated polyolefin, alkanol, and hydrocarbon used. For the preferred
20 Glissopal®1000, a mixture of 17.5 percent by weight (% w/w) ethanol and 82.5% w/w of hexane proved to be suitable. The amount of low-molecular weight unsaturated polyolefin that can be used per quantity of said solvent depends on its solubility, the viscosity of the solution/dispersion tolerated by the equipment, and the solubility of the ozonated product. However, because the
25 alkanol participates in the reaction of the ozone with the unsaturated end groups to form alkoxyhydroperoxides, it is preferred to use so much solvent and low-molecular weight unsaturated polyolefin that the molar ratio of -OH groups of the alcohol to unsaturated groups of the polyolefin ranges from 0.5 to 50,

preferably from 1 to 40, and most preferably from 2 to 20.

The crude hydrocarbon/alcohol solutions/dispersions of alkoxyhydroperoxides are reacted further in step 2 with hydrogen to form low-molecular weight polyolefins with hemiacetal or hemiketal end groups. It is estimated that the alkoxyhydroperoxide concentration may vary from 1-30% w/w. The balance of the solution typically consists of the hydrocarbon, residual low-molecular weight unsaturated polymer, and side products of the first step. The preferred amount depends, *inter alia*, on the solubility of the alkoxyhydroperoxide raw material and the hemiacetal product. Suitably, a solution/dispersion with 5-20% w/w of alkoxyhydroperoxides and 10-20% w/w of alkanol in the hydrocarbon is used.

The catalyst to be used in this process step can be selected from common precious metal reduction catalysts. Those may be applied coated on a porous support or as such in powdered. Porous supports in this embodiment may be activated charcoal, alumina, silica gel or diatomaceous earth. Preferably a conventional platinum or palladium catalyst, without a porous support, is used and conventional process conditions applied. The hydrogen pressure applied can be from 0.1 to 5 bara. Typically, a conversion of close to 100% and a selectivity of close to 100% are attainable using a hydrogen pressure of 1.5 bar absolute (bar or bara) and an (average) contact time of 30 minutes at 30°C. This process step is preferably conducted in a continuous fashion as well and in combination with the ozonation step described above.

As it has been already described in EP 0 099 981 A1 and US 3, 705,922, alkoxyhydroperoxides are reduced by the action of hydrogen and the aid of a precious metal catalyst to form hemiacetals and/or hemiketals. As NMR spectroscopic measurements have shown this holds true for the current PIB-

alkoxyhydroperoxides as well.

In step 3 the catalyst is filtered out of the product mixture resulting from step 2. Preferably, the catalyst is recycled to step 2. Optionally, the product is then
5 washed in a conventional way, in one or more washing steps, to remove the side products formed in any of the previous steps, such as formaldehyde, formic acid, and acetone. Preferably, the wash is conducted with water or an alkanol as used in step 1 or 2. If washed, also the alkanol of step 2 may be removed from the mixture. Most preferably, water is used in at least the last
10 washing step. Preferably, the washing is conducted in such a fashion that all acidic side products are removed, since such acidic material can interfere in the following process step. Consequently, it may be preferred to use an alkaline reagent, such as sodium hydroxide or sodium bicarbonate, in one or more of the washing fluids to ensure the removal of acid. Typically, the washing step is
15 conducted at ambient temperature for a period of 5 to 60 minutes.

In step 4 the hemiacetal hemiketal mixture is aminated with ammonia, or higher primary or secondary amines, and hydrogen. Preferably, ammonia and hydrogen are used. If so desired, use is made of higher primary or secondary
20 amines, which can be selected from any hydrocarbyl mono-, di-, or polyamine. The higher primary amines may contain further nitrogen atoms, for example in the form of a (further) secondary amine moiety. Suitable hydrocarbyl amines include: alkylamine, such as methylamine, ethylamine, propylamine, isopropylamine, butylamine, isobutylamine, isomers of hexylamine, isomers of
25 coco amine, and isomers of (hydrogenated) tallow amine; alkylene diamine, such as ethylene diamine, propylene diamine, isopropylene diamine, butylene diamine, isobutylene diamine, and isomers of hexamethylene diamine; dialkylene triamine, such as diethylene triamine, dipropylene triamine,

diisopropyl triamine, isomers of dibutyl triamine, and isomers of dihexyl triamine; trialkylene tetramine, such as triethylene tetramine and isomers of tripropylene tetramine; tetraalkylene pentamine, such as tetraethylene pentamine; pentalkylene hexamine, such as pentaethylene hexamine; o-, m-, or p-phenylene diamine; alkyl substituted o-, m-, or p-phenylene diamine; dialkyl aminoalkylamine, such as dimethyl aminomethylamine, dimethyl aminoethylamine, dimethyl aminomethylamine, dimethyl aminopropylamine, dimethyl aminobutylamine, dimethyl aminohexylamine, diethyl aminomethylamine, diethyl aminoethylamine, diethyl aminopropylamine, diethyl aminobutylamine, diethyl aminopentylamine, diethyl aminohexylamine, dipropyl aminomethylamine, dipropyl aminoethylamine, dipropyl aminopropylamine, dipropyl aminobutylamine, dipropyl aminopentylamine, and dipropyl aminohexylamine; aniline; alkylene aniline, including products like methylene dianiline and dimethylene trianiline; polyalkylene aniline; and secondary amines of the general formula R^1NHR^2 where R^1 and R^2 may be independently selected from cyclic, straight, branched, and/or unbranched alkyl, heteroalkyl, aromatic or heteroaromatic groups.

In this step a conventional catalyst and conventional conditions are employed. Good results were obtained using a preferred catalyst, viz. palladium on an activated carbon support. Hydrogen pressures of 5 to 50 bara, preferably 10-30 bara, were suitable. If ammonia is used, the ammonia pressure can be selected from 10 to 50 bara, preferably 20-40 bara. An ammonia pressure of about 25 bara was used with success. The process temperature can range from 50 to 200°C. At higher temperatures faster reaction rates were observed. However, a higher temperature is more demanding on the equipment that is used. Therefore, it is preferred to use a reaction temperature of 75-150°C, more preferably 100-150°C. A temperature of about 140°C is most preferred.

Reaction times may be as long as 20 hours. Preferably, the reductive amination is conducted in a continuous fashion.

5 Reductive amination can be employed using a solution/dispersion of the hemiacetal. To facilitate the reaction, it is preferred to work in a solution. Preferably, the solvent comprises an hydrocarbon alkanol mixture. More preferably, an hydrocarbon alkanol mixture as presented for step 1 is used. Most preferably, the hydrocarbon alkanol mixture is the same as the hydrocarbon alkanol mixture used in step 2. The alkanol of the previous steps
10 typically is still present. If so desired, further alkanol may be added to the mixture. In that case it is preferred to use the alkanol of step 1.

In the last step, the catalyst used in the reductive amination step is removed, typically by filtration. Preferably, the catalyst is recycled to step 4. The resulting
15 product, which may be in the form of a solution/dispersion, can be used as is, or it may be subjected to a further step to remove part or all of the solvent. Suitably a distillation step is used to remove most of the solvent. Preferably, the distillation is performed under reduced pressure.

20 Preferably, the process is conducted in a continuous fashion, using a cascade of three or more reaction vessels, optionally together with one or more holding and/or washing vessels, in which the ozonolysis, the reduction, and the reductive amination are performed in series.

25 It is noted that the aminated olefinic products obtained are partly of the same type as the products obtained by the process of EP-A-0 123 424.

A second embodiment of the invention is the use of the aminated olefinic


products obtained by the process of the first embodiment as a fuel and lubricating oil additive. Preferably, the aminated olefinic products are used as an additive in fuels for combustion engines. In such a use they were found to reduce or prevent the formation of deposits on the valves and cylinder walls of the engine in which the fuel is used. Depending on the conditions, the detergent properties of the aminated olefinic products can be such that even existing deposits are removed. Any fuel or lubricating oil can be used with the products of the invention. Preferred fuels include oil fractions ranging from kerosene to diesel. If used in lubricating oils, the oil may be any suitable lubricating oil, including those based on naphthalene, paraffin, other hydrocarbons, synthetic oils, or derived from coal products. Synthetic oils are known to include alkylene polymers, alkylene oxide polymers, dicarboxylic acid esters, silicon products, and the like.

In fuels, the aminated olefinic products are typically used in an amount of 10 to 2,000 mg/kg. Preferably, they are used in an amount of 50-400 mg/kg, more preferably in an amount of 75-200 mg/kg. In lubricating oils, they are typically used in an amount of 0.05-25% by weight.


Experimental

The following chemicals were used:

Glissopal® 1000 ex BASF, being about 75% w/w of



and about 25% w/w of



, with n

being such that the number averaged weight of the product is 1,000.

Hydrogen 99.9% ex BOC Cylinder Gas N.V., Herenthout

Ammonia 99.9% ex BOC Cylinder Gas N.V., Herenthout

NaHCO₃ 99.5 % ex Merck KGaA, Darmstadt

Ethanol 99.9 % containing 1 % Petrolether ex Fa. Martin u. Werner-Mundo

Hexane, pure Merck 104368

Water = demineralized

Platinum (Adams) catalyst for step 2 PtO₂ ex Aldrich 20,603-2

- 5 Palladium on activated carbon reductive amination catalyst type 39 ex Johnson
Matthey 5 % Pd, water content 59.1 %

Ozone was produced from oxygen 99.5 % ex BOC Cylinder Gas N.V.,
Herenthout, on-site using an ozone generator ex Fischer with an ozone
capacity of 50 g/m³ oxygen

10

Example 1

- A standard glass coil cooler with a length of 30 cm is used as the ozonization
reactor. The temperature of the coil was controlled at 0°C by circulating cooling
fluid through the cooler around the coil. The coil cooler was mounted on a
15 three-necked flask of 100 ml, which served as a holding vessel. Ozone
containing oxygen gas from the generator was pumped through the flask up
through the coil at a rate of 1.17 l/min. The ozone thus pumped through the coil
was 1.25 mmol/min. A Glissopal® 1000 solution was fed at the top of the coil at
a rate of about 3.5 g/min. The solution contained 60% w/w of hexane, 27% w/w
20 of Glissopal® 1000, and 13% w/w of ethanol. The countercurrent thus attained
resulted in a conversion of >95% of the unsaturated groups of the Glissopal®.

- From the three-necked flask, the alkoxyhydroperoxide-containing solution was
pumped into a stirred, cylindrical, thermostatted, glass vessel at a rate of about
3.5 g/min. Hydrogen was introduced into the vessel at a rate of about 0.6
25 mmol/min to maintain a hydrogen pressure of 1.5 bara. At the start of the
process, the vessel had been charged with 2 g of platinum (Adams) catalyst
and 100 ml of hexane. During the reaction, the vessel was stirred vigorously.
Product was withdrawn from the reactor at a rate of about 3.5 g/min. Without

cooling, the temperature was 35°C after reaching a steady state.

In this example, washing was conducted batchwise, using a separating funnel, by extracting 500 ml of the product mixture with: i) 200 ml of water, ii) 200 ml of water saturated with NaHCO₃, and iii) water. The resulting product was dried over anhydrous sodium sulfate. The dried product was diluted with 40 ml of ethanol.

The reductive amination was conducted in a 1 l steel autoclave ex Büchi, with a hollow shaft gas turbine stirrer (stirrer speed 1000-1200 min⁻¹) and a bottom outlet provided with a filter. The autoclave was charged with 250 ml ethanol, 20.0 g of a 5% palladium catalyst on activated carbon, and subsequently purged first with nitrogen and secondly with hydrogen. The catalyst was activated by heating the contents of the autoclave to 125°C while maintaining a hydrogen pressure of 40 bara. The activated catalyst was washed twice with 200 ml ethanol and subsequently suspended in 200 ml hexane.

For the reductive amination, the temperature was maintained at 145°C. First 1.0 mole of anhydrous ammonia was added, then all of the washed and dried hemiacetal solution. Thereafter hydrogen was added in an amount such that the overall pressure was 40 bara. The reaction was allowed to run for 20 hours. Filtered product solution was obtained through the bottom outlet.

Solvent vaporation at reduced pressure resulted in a colourless viscous oil. Analysis with conventional wet analytical, GPC, NMR, and MALDI-TOF techniques confirmed the structure to consist of the aminated low-molecular weight polyisobutene, the remainder being a mixture of hexane (4% w/w), unreacted Glissopal® (5% w/w), and low-molecular weight polyisobutenes with oxidic functionality, such as alcohol, acid, and hemiacetal. The overall yield of aminated product in this unoptimized example was 68% on Glissopal.

Examples 2-4

The previous example was repeated, but the temperature during the reductive amination was controlled at 80°C, 120°C, and 145°C, respectively.

The yield of aminated product in these examples was 45, 56, and 68% w/w on
5 Glissopal, respectively.

Claims

1. Process to make aminated polyolefins involving the steps of:
 - ozonolysis of one or more low-molecular weight polyolefins with at least
5 one end group that is unsaturated, in the presence of an alkanol-
hydrocarbon mixture, to form polyolefin-alkoxyhydroperoxides,
 - catalytic reduction of the polyolefin-alkoxyhydroperoxides with hydrogen
and a suitable catalyst, to form a mixture of hemiacetals and hemiketals,
in the presence of a solvent,
 - 10 - removal of the catalyst and optional washing of the mixture resulting
from step 2, to remove undesired side products,
 - reductive amination of the hemiacetal hemiketal mixture in order to form
the aminated polyolefin end product, optionally in the presence of a
solvent, and
 - 15 - removal of the catalyst and optional removal of the solvent.
2. Process of claim 1 wherein a low-molecular weight polyolefin with just one
unsaturated end group is used.
- 20 3. Process according to claim 1 or 2 wherein ammonia is used in the reductive
amination step.
4. Process according to claim 1 or 2 wherein a higher primary or secondary
amine is used in the reductive amination step.
- 25 5. Process according to any one of the preceding claims wherein the low-
molecular weight polyolefin comprises a low-molecular weight
polyisobutylene.

6. Process according to claim 5 wherein the number averaged molecular weight of the polyisobutylene is from 500-1250 Dalton.
- 5 7. Process according to any one of the preceding claims wherein one or more of the process steps are conducted in a continuous fashion.
8. Process according to claim 6 wherein each step is conducted in a continuous fashion, using cascaded reactors, optionally supplemented with
10 holding and/or washing vessels.
9. Use of the aminated low-molecular weight polyolefins resulting from the process of any one of claims 1-7 in lubricating oil and/or fuel compositions to reduce, prevent, and/or reverse the formation of deposits on valves and/or
15 cylinder walls of combustion engines in which said fuel and/or oil is used.

INTERNATIONAL SEARCH REPORT

In national Application No

PCT/EP 01/00467

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08F8/32

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08F C10L C10M

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

PAJ, WPI Data, EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	EP 0 389 722 A (BP CHIMIE S.A.) 3 October 1990 (1990-10-03) column 1, line 1 - line 3; claims 1-8	1-9
Y	US 5 103 061 A (J. R. BLACKBOROW) 7 April 1992 (1992-04-07) cited in the application the whole document	1-9
Y	EP 0 882 782 A (THE LUBRIZOL CORPORATION) 9 December 1998 (1998-12-09) page 8, line 55 -page 10, line 27 page 12, line 5 -page 13, line 16; claims 1-28	1-9

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *Z* document member of the same patent family

Date of the actual completion of the international search

16 May 2001

Date of mailing of the international search report

28/05/2001

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Permentier, W

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 01/00467

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	GB 1 172 818 A (MONSANTO COMPANY) 3 December 1969 (1969-12-03) cited in the application claims 1-20 -----	1
A	WO 95 17440 A (MONSANTO COMPANY) 29 June 1995 (1995-06-29) claims 1-53 -----	1
A	US 3 931 024 A (SHIH-EN HU) 6 January 1976 (1976-01-06) claims 1-11 -----	1
A	EP 0 781 793 A (CHEVRON CHEMICAL COMPANY) 2 July 1997 (1997-07-02) claims 1-10 -----	1
A	US 5 424 356 A (D. K. PARKER) 13 June 1995 (1995-06-13) claims 1-9 -----	1
A	FR 975 461 A (DU PONT DE NEMOURS AND COMPANY) 6 March 1951 (1951-03-06) page 10 -----	1

INTERNATIONAL SEARCH REPORT

Information on patent family members

In International Application No

PCT/EP 01/00467

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 389722	A	03-10-1990	NONE	
US 5103061	A	07-04-1992	EP 0384086 A	29-08-1990
			AT 95809 T	15-10-1993
			AU 622286 B	02-04-1992
			AU 5028690 A	05-09-1990
			BR 9005079 A	06-08-1991
			CA 2009557 A	10-08-1990
			DE 69003897 D	18-11-1993
			DE 69003897 T	10-02-1994
			DK 411084 T	14-02-1994
			EP 0411084 A	06-02-1991
			ES 2045907 T	16-01-1994
			WO 9009371 A	23-08-1990
			HU 208666 B	28-12-1993
			JP 3504505 T	03-10-1991
			NO 904210 A,B,	27-09-1990
			SG 123693 G	25-02-1994
			ZA 9000872 A	30-10-1991
EP 882782	A	09-12-1998	AU 6983898 A	10-12-1998
			BR 9802266 A	02-05-2000
			CA 2239633 A	05-12-1998
			JP 11071592 A	16-03-1999
			SG 70085 A	25-01-2000
GB 1172818	A	03-12-1969	DE 1645056 A	14-05-1970
			FR 1522252 A	05-08-1968
			SE 348186 B	28-08-1972
WO 9517440	A	29-06-1995	US 5559193 A	24-09-1996
			AT 167685 T	15-07-1998
			AU 679801 B	10-07-1997
			AU 8127894 A	10-07-1995
			BR 9408364 A	26-08-1997
			CA 2178649 A	29-06-1995
			CN 1142836 A	12-02-1997
			CZ 9601741 A	16-10-1996
			DE 69411285 D	30-07-1998
			DE 69411285 T	11-02-1999
			EP 0736048 A	09-10-1996
			HU 75292 A	28-05-1997
			JP 9506925 T	08-07-1997
			SK 76096 A	09-04-1997
US 3931024	A	06-01-1976	NONE	
EP 781793	A	02-07-1997	CA 2191919 A	20-06-1997
			DE 69608401 D	21-06-2000
			DE 69608401 T	11-01-2001
			EP 0781794 A	02-07-1997
			JP 9221545 A	26-08-1997
US 5424356	A	13-06-1995	AU 1967395 A	09-10-1995
			BR 9507160 A	09-09-1997
			CA 2121638 A	22-09-1995
			DE 69509378 D	02-06-1999
			DE 69509378 T	14-10-1999

INTERNATIONAL SEARCH REPORT

*Information on patent family members

In International Application No

PCT/EP 01/00467

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5424356 A		EP 0751975 A	08-01-1997
		JP 9510498 T	21-10-1997
		WO 9525768 A	28-09-1995
		US 5442009 A	15-08-1995
		US 5442007 A	15-08-1995
FR 975461 A	06-03-1951	NL 76601 C	